



Corporate Headquarters  
1901 Mason Ave, Suite 101  
Daytona Beach, FL 32117

Toll Free: 800.549.2539  
Phone: 386.274.1382  
[www.adsil.com](http://www.adsil.com)

## **ASTM B-117 TEST REPORT**

**LAB REFERENCE:** LR20-822 Addendum

**CUSTOMER:** Adsil

**COATING SYSTEM:** Coated Aluminum Q-Panel submitted for testing.  
Panel labelled as MG1-3500

### **Salt Spray (Fog) Resistance**

Test specimen was tested in accordance with ASTM B117.  
Atlas Model SF850 Corrosion Fog Exposure System was used for testing, with a Sodium Chloride solution at 5%.

Result: After 20,300 hours exposure the test sample is performing extremely well.  
Sample is continuing testing as of this report.

Report Date: March 29, 2022  
Prepared By: Paul Lemke  
Product Manager